


## **CRESWICK WOOLLEN MILLS PERSONAL PROTECTION BLANKETS**

Email: sales@creswickwool.com.au



### OUR BLANKETS UNDER FIRE

#### W20 Black Blanket

Fabric Composition- 95% Wool/ 5% Flame Retardant Synthetic

Blanket Size- 165cm x 210cm

Testing by ISO Standards in accordance with  
CFA Specification Personal Protective Blankets

AS2001.2.13 Mass Per Unit Area- 550gsm

### FABRIC TESTING

This test observes behaviour after application of Flame  
ISO 17493:2016- Tested at 180C as per requirements of  
AS/NZS4824:2009 Wildland Firefighting Specification and  
CFA Personal Protective Blanket Specification

No Ignition of the Blanket

No Melting of the Blanket

No Dripping of the Blanket

No Charring of the Blanket

No Splitting, Deformation or holes in the Blanket

**CFA requires Blanket not to shrink more than 5%**

Test Result- Blanket shrunk under 180C less than 3%

This test identifies strength after application of Flame

ISO 15025 .8.2.1.3.(g) No Hole develops after application of flame

ISO 15025 .8.2.1.3.(b) No afterflame after application of flame